CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/MM/W.No.17/2017-18 Date: 07.09.2017

TEST REPORT

CLIENT	:	**Executive Engineer,** Rajarajeshwari Nagar Division, BBMP, Bangalore.
AGENCY	:	**Sri. M. Manjunath,** Contractor, Bangalore.
NAME OF THE WORK	:	Construction of Shops adjoining to Muthylanagara Bus Bay in Ward No.17, BBMP, Bangalore.
SAMPLE ID	:	Cement
SAMPLES SUPPLIED BY	:	AGENCY

The results of the tests conducted on the cement sample are as follows:

Sl.No	Descriptions	Test Method as per IS	Test Result	Requirements as per IS: 12269-1987
1	a) Initial Setting Time	IS-4031 (Part -5)	140 Minutes	Not Less than 30 Minutes
	b) Final Setting Time	IS-4031 (Part -5)	390 Minutes	Not More than 600 Minutes
2	Soundness	IS-4031 (Part 3) by the Le-Chatelier method	1 mm	Not more than 10 mm
3	Standard Consistency	IS-4031 (Part -4)	30.00 %	-

Note:

⇒ The report shall not be reproduced, except in full, without the written approval of the laboratory.

⇒ The results indicated above are based on the tests carried out on the samples received in the laboratory.

⇒ Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Lab No.: CQCE/BBMP/MM/W.No.17/2017-18 Date : 07.09.2017

TEST REPORT ON FINE AGGREGATES (SAND)
IS 383-1970 (RA- 2002)

Client : **Executive Engineer,** Rajarajeshwari Nagar Division, BBMP, Bangalore.
Agency : **Sri. M. Manjunath,** Contractor, Bangalore.
Name of Work : Construction of Shops adjoining to Muthylanagara Bus Bay in Ward No.17, BBMP, Bangalore.
Date of Testing : 07.09.2017
Material : Sand Total wt. of aggregates in gms = 1000

Is Sieve Size in mm	Weight Retained (gm)	Retained Weight in %	Cumulative Retained Weight in %	Cumulative Weight Passing in %	Spec.Limits For Zone-II
10	0	0	0	100	100
4.75	71	7.10	7.10	92.9	90-100
2.36	116	11.60	18.70	81.3	75-100
1.18	225	22.50	41.20	58.8	55-90
600 Micron	173	17.30	58.50	41.5	35-59
300 Micron	198	19.80	78.30	21.7	8-30
150 Micron	141	14.10	92.40	7.6	0-10

Note:
1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Lab No.: CQCE/BBMP/MM/W.No.17/2017-18 Date : 07.09.2017

TEST REPORT ON COARSE AGGREGATES
IS 383-1970 (RA- 2002)

Client : **Executive Engineer,** Rajarajeshwari Nagar Division, BBMP, Bangalore.
Agency : **Sri. M. Manjunath,** Contractor, Bangalore.
Name of Work : Construction of Shops adjoining to Muthylanagara Bus Bay in Ward No.17, BBMP, Bangalore.
Date of Testing : 07.09.2017
Material : 40mm Aggregates

Total wt. of aggregates in gms = 15000

Is Sieve Size in mm	Weight Retained (gm)	Retained Weight in %	Cumulative Retained Weight in %	Cumulative Weight Passing in %	Spec.Limits
80	0	0	0	100	100
40	381	2.54	2.54	97.46	95-100
20	7561	50.41	52.95	47.05	30-70
10	4163	27.75	80.70	19.30	10-35
4.75	2374	15.83	96.53	3.47	0-5

Note:
1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

b No: CQCE/BBMP/MM/W.No.17/2017-18 Date: : 07.09.2017

TEST REPORT ON COARSE AGGREGATES
IS 383-1970 (RA- 2002)

lient : **Executive Engineer,** Rajarajeshwari Nagar Division, BBMP, Bangalore.
gency : **Sri. M. Manjunath,** Contractor, Bangalore.
Name of Work : Construction of Shops adjoining to Muthylanagara Bus Bay in Ward No.17, BBMP, Bangalore.
Date of Testing : 07.09.2017
Material : 20mm Aggregates

Total wt. of aggregates in gms = 5000

Is Sieve Size in mm	Weight Retained (gm)	Retained Weight in %	Cumulative Retained Weight in %	Cumulative Weight Passing in %	Spec.Limits
40	0	0	0	100	100
20	177	3.5	3.5	96.5	95-100
10	2564	51.3	54.8	45.2	25-55
4.75	1986	39.7	94.5	5.5	0-10

Note:
1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/MM/W.No.17/2017-18

Date: 11.09.2017

TEST REPORT

CLIENT	:	**Executive Engineer,** Rajarajeshwari Nagar Division, BBMP, Bangalore.
AGENCY	:	**Sri. M. Manjunath,** Contractor, Bangalore.
NAME OF THE WORK	:	Construction of Shops adjoining to Muthylanagara Bus Bay in Ward No.17, BBMP, Bangalore.
SAMPLE ID	:	Bricks Test – Class 5.0
SAMPLES SUPPLIED BY	:	AGENCY

The results of the tests conducted on the samples are as follows:

Sl. No	Description	Test method as per IS Codes	Result	Requirement as per IS 1077-1992 (Rev-5)
1	Compressive Strength Of Bricks	IS 3495-1992 (Part-1)	5.17 N/mm²	Class designation 5.0
2	Water Absorption of Bricks	IS 3495-1992 (Part – 2)	12.83 %	Not more than 20 %
3	Efflorescence of Bricks	IS 3495-1992 (Part – 3)	Moderate	Up to 12.5 Class
4	Dimensional Analysis of Bricks (minimum Sampling is 20 Nos.)	IS 1077-1992 (Rev – 5)		
(a)	Measurement of Length in mm		3820 mm	(3800 ± 80 mm)
(b)	Measurement of Width in mm		1816 mm	(1800 ± 40 mm)
(c)	Measurement of Height in mm		1425 mm	(1400 ± 40 mm)

Note:

⇒ The report shall not be reproduced, except in full, without the written approval of the laboratory.

⇒ The results indicated above are based on the tests carried out on the samples received in the laboratory.

⇒ Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/MM/W.No.17/2017-18 Date: 08.09.2017

TEST RESULTS OF PHYSICAL PROPERTIES OF REINFORCEMENT STEEL

Client : **Executive Engineer,** Rajarajeshwari Nagar Division, BBMP, Bangalore.
Agency : **Sri. M. Manjunath,** Contractor, Bangalore.
Name of Work : Construction of Shops adjoining to Muthylanagara Bus Bay in Ward No.17, BBMP, Bangalore.
Sample Identification : 8mm,10mm,12mm,16mm, Fe 500 TMT Bars
Technical Reference : IS 1786:2008, IS 1608:2005, IS 1599:1985 (Reaffirmed 2006)
Date of test : 08.09.2017

S.No	Brand	Nominal size (dia in mm)	Mass per metre (kg/metre)	TENSILE STRENGTH		
				0.20 % proof stress/ yield stress (N/mm^2)	Tensile strength (N/mm^2)	Elongation, percent on gauge length
1	Fe 500	8	0.38	536	544	14
2	Fe 500	10	0.63	548	556	15.5
3	Fe 500	12	0.89	561	569	16.5
4	Fe 500	16	1.58	572	580	17

Remarks:
1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory
3. Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/MM/W.No.17/2017-18 Date: 15.09.2017

TEST REPORT ON CEMENT MORTAR CUBES

Client	: **Executive Engineer,** Rajarajeshwari Nagar Division, BBMP, Bangalore.
Contractor	: **Sri. M. Manjunath,** Contractor, Bangalore.
Name of the work	: Construction of Shops adjoining to Muthylanagara Bus Bay in Ward No.17, BBMP, Bangalore.
Sample ID	: Cement Mortar
Size of cubes	: 70.6mmx70.6mmx70.6mm
Cross Sectional Area	: 5000 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
Compressive Strength as on	: 7th day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	08.09.2017	15.09.2017	0.886	176.3	35.26
2	08.09.2017	15.09.2017	0.884	182.5	36.50
3	08.09.2017	15.09.2017	0.881	179.4	35.88

Note:
1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.: CQCE/BBMP/MM/W.No.17/2017-18 Date: 15.09.2017

TEST REPORT ON CEMENT MORTAR CUBES

Client	: **Executive Engineer,** Rajarajeshwari Nagar Division, BBMP, Bangalore.
Contractor	: **Sri. M. Manjunath,** Contractor, Bangalore.
Name of the work	: Construction of Shops adjoining to Muthylanagara Bus Bay in Ward No.17, BBMP, Bangalore.
Sample ID	: Cement Mortar
Size of cubes	: 70.6mmx70.6mmx70.6mm
Cross Sectional Area	: 5000 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
Compressive Strength as on	: 7th day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	08.09.2017	15.09.2017	0.888	179.5	35.90
2	08.09.2017	15.09.2017	0.891	172.6	34.52
3	08.09.2017	15.09.2017	0.894	169.2	33.84

Note:
1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 15 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.:CQCE/BBMP/MM/W.No.17/2017-18

22.09.2017

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client	**: Executive Engineer,** Rajarajeshwari Nagar Division, BBMP, Bangalore.
Agency	**: Sri. M. Manjunath,** Contractor, Bangalore.
Name of the work	: Construction of Shops adjoining to Muthylanagara Bus Bay in Ward No.17, BBMP, Bangalore.
Sample ID	: Cement Concrete
Size of cubes	: 150mmx150mmx150mm
Cross Sectional Area	: 22500 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
Grade of Concrete	: M_{20}
Compressive Strength as on	: 7th day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	15.09.2017	22.09.2017	8.162	325.2	14.45
2	15.09.2017	22.09.2017	8.186	346.7	15.41
3	15.09.2017	22.09.2017	8.160	371.4	16.51

Note:
1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner

CIVIL QUALITY CONSULTANTS & ENGINEERS

(Buildings Geo-Tech & Highway Materials Testing Laboratory)
An ISO 9001: 2008 Certified Company

JAS-ANZ
ISO 9001:2000 CERTIFIED

Job No.:CQCE/BBMP/MM/W.No.17/2017-18 13.10.2017

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

Client	: **Executive Engineer,** Rajarajeshwari Nagar Division, BBMP, Bangalore.
Agency	: **Sri. M. Manjunath,** Contractor, Bangalore.
Name of the work	: Construction of Shops adjoining to Muthylanagara Bus Bay in Ward No.17, BBMP, Bangalore.
Sample ID	: Cement Concrete
Size of cubes	: 150mmx150mmx150mm
Cross Sectional Area	: 22500 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
Grade of Concrete	: M_{20}
Compressive Strength as on	: 28th day

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	15.09.2017	13.10.2017	8.253	525.3	23.35
2	15.09.2017	13.10.2017	8.261	539.1	23.96
3	15.09.2017	13.10.2017	8.282	487.5	21.67

Note:
1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

For CIVIL QUALITY CONSULTANTS & ENGINEERS

Authorised Signatory

Office & Laboratory : # 133, Bhuvaneshwarinagar, Dodda Basti Main Road, Bangalore - 560 056.
e-mail:civilqualityconsultants@gmail.com Ph: 080-23240644 / Mob: 8553518550

Scanned by CamScanner